A-Cast Acrylic Material Safety Data Sheet

1. INDENTIFICATION OF THE SUBSTANCE/ PREPARATION AND COMPANY/ UNDERTAKING

Product Name: A-CAST EG ACRYLIC SHEET

Address: : A&C Plastics 6135 Northdale Houston, TX 77087

Phone No. : (800) 231-4175

2. COMPOSITION/ INFORMATION ON INGREDIENTS

PRODUCT DESCRIPTION

A high molecular weight acrylic sheet used in a wide range of applications. Methyl methacrylate : greater than 90%.

HAZARDOUS INGREDIENT (S) No classifiable hazardous ingredient (s) CAS No. EC No. EC Classification

3. HAZARDS INDENTIFICATION

Low toxicity under normal conditions of handling and use. Thermal decomposition will evolve toxic, Irritant and flammable vapours. Care should be taken during thermoforming to ensure that the product is not exposed to temperatures exceeding 200°C.

Certain machining operations eg. Laser cutting, can give rise to toxic and corrosive furmes. Adequate ventilation MUST be used.

4. FIRST AID MEASURES

Ingestion:

Material is not expected to be harmful by ingestion. No special first aid measures are required.

Skin Contact: Wash immediately with plenty of water and soap.

Eye Contact: Rinse immediately with plenty of water for at least 15 minutes.

Inhalation: Material is not expected to be harmful if inhaled. Remove to fresh air.

5. FIRE - FIGHTING MEASURES

Extinguishing Media:



800.231.4175 ACPlasticsInc.com

Page I of 4

A-Cast Acrylic Material Safety Data Sheet

Use water spray or fog, carbon dioxide or dry chemical.

Protective Equipment: Firefighters, and other exposed, wear self - contained breathing apparatus.

Fire Rating:

Classed as DIN4102 : B2, with no burning droplets NF92500+ : M4(no droplets) BS476 Part 7: Class 3 BS2782 method 508A: TP(b)

UL Flammability: UL94HB

6. ACCIDENTAL RELEASE MEASURES

Offcuts, swarf or dust should be collected and disposed of in a safe way.

7. HANDLING AND STORAGE

7.1 HANDLING

These sheets are heavy and unwieldy. They should be handled with care, particularly in windy locations or outdoors.

If broken or chipped the resultant edges can be sharp and cause cuts to skin and eyes.

Take precautionary measure against static discharges.

Process Hazards

All polymers degrade to some extent at their processing temperature, an effect which increases with increasing temperature.

Under normal conditions where thermoforming temperatures will not exceed 200°C thermal decomposition product will include methyl methacrylate.

Certain machining operation eg laser cutting can give rise to toxic and corrosive fumes. Adequate ventilation MUST be used.

7.2 STORAGE

Keep away from heat. Store vertically on A-frames

Storage Temperature : Below 40°C

8. EXPOSURE CONTROLS/ PERSONAL PROTECTION

Provide adequate ventilation, including appropriate local extraction if dusts, fumes or vapours are likely to be evolved.

Consideration should be given to the work procedures involved and the potential extent of exposure as they may determine whether a higher level of protection is required.

Local extraction close to the cutting head must be used when laser cutting. When suitable engineering



800.231.4175 ACPlasticsInc.com

A-Cast Acrylic Material Safety Data Sheet

controls are not fitted or are inadequate, wear suitable protective equipment.

The following information is given as general guidance.

Respirators: NORMAL HANDLING:

Not normally required.

PROCESSING:

Dust: A suitable dust mask or dust respirator with filter type P may be appropriate. mask mask with filter type A may be appropriate. (EN141/ EN143).

Eye ProtectionWear eye/ face protection. Safely spectacles/ goggles/ full face shield.

Gloves: Sharp edges may cause cuts. Wear Suitable gloves.

9. PHYSICAL AND CHEMICAL PROPERTIES

Form:	Sheet
Colour:	Clear or Coloured
pH (Value):	Not applicable
Boiling Point (°C):	Not applicable
Melting Point (°C):	Not applicable
Flash Point (°C):	11.5 (MMA). Sheet has no flash point.
Flammable Limits:	Not applicable

Auto Ignition Temperature (°C): 421 (MMA)

S

Decomposition Temperature (°C): Will not decompose below 200°C

Freezing Point (°C):	Not applicable
Softening Point (°C):	>100
Viscosity (mPa.s):	solid

10. STABILITY AND REACTIVITY

Hazardous Reactions: None known Hazardous Decomposition Product (s): Methyl methacrylate, traces of Acrolein.

11.TOXOLOGICAL INFORMATION

Inhalation Unlikely route of exposure.



800.231.4175 ACPlasticsInc.com Skin Contact

No evidence of irritant effects from normal handling and use. Sharp edges may cause cuts.

Eye Contact

Swarf or dust may cause irritation. Sharp off-cuts may cause eye damage.

Ingestion Unlikely to behazardous if swallowed.

Long Term Exposure No known hazards are associated with the use of this material.

12.ECOLOGICAL INFORMATION

Environmental exposure from substances of this preparation are limited due to the physical form of the product.

This material is not classified as dangerous for the environment.

13.DISPOSAL CONSIDERATIONS

Disposal should be in accordance with local, state or national legislation. Incrineration may be used to recover energy value. Bury on an authorised landfill site or incinerate under approved controlled conditions, using incinerators suitable for the disposal of noxious chemical waste. Large quantities of waste may be recoverable.

14.TRANSPORT INFORMATION

Not Classified as Dangerous for Transport.

15.REGULATORY INFORMATION

Not Classified as Dangerous for Supply/ Use.

- EC Classification: Under the Classification, Packaging and Labelling of Dangerous Substances Rags, 1984, this material is not dengerous for supply or conveyance.
- 16. This information has been compiled from sources considered to be dependable and is, to the best of our knowledge, accurate and reliable as to the data compiled.

However, no guarantee or warranty is made to its accuracy, reliability and/ or completeness. It is the user's responsibility to satisfy himself as to the fitness or suitability of the product for the intended particular purpose or use. All risk of the use of the product are therefore assumed by the user. Appropriate warnings and safe handling procedures should be provided to handlers and users.



800.231.4175 ACPlasticsInc.com