

Standard Light Transmission Specifications for Acrylic Mirror

| Color | Nominal Thickness | Light Transmission % |
|-----------------|-------------------|----------------------|
| 1000 Blue | .118 | 67%, +/- 2% |
| 1020 Purple | .118 | 29%, +/- 2% |
| 1050 Grey | .118 | 40%, +/- 2% |
| 1119 Orange | .118 | 36%, +/- 2% |
| 1300 Gold | .118 | 84%, +/- 2% |
| 1400 Red | .118 | 9%, +/- 2% |
| 1402 Copper | .118 | 19%, +/- 2% |
| 1450 Pink | .118 | 64%, +/- 2% |
| 1600 Bronze | .118 | 58%, +/- 2% |
| 2069 Blue | .118 | 52%, +/- 2% |
| 2120 Teal | .118 | 33%, +/- 2% |
| 2208 Yellow | .118 | 81%, +/- 2% |
| 2414 Green | .118 | 59%, +/- 2% |
| 2422 Amber | .118 | 49%, +/- 2% |
| 2423 Red | .118 | 5%, +/- 2% |
| 2424 Blue | .118 | 9%, +/- 2% |
| 1310 Red | .116 | 23%, +/-2% |
| 4674 Green | .117 | 23%, +/-2% |
| 6352 "NFL" Blue | .118 | 5%, +/- 0.5% |
| See-thru Mirror | CLEAR | 5% to 20% |
| See-thru Mirror | BRONZE | 5% to 14% |
| | | |