



Typical Properties

<u>CONDITIONS</u>	<u>TEST METHOD</u>	<u>UNIT</u>	<u>VALUE</u>
<u>GENERAL PROPERTIES</u>			
Density	ISO 1183	gr/cm ³	1,27
Water Absorbtion (23 °C, 24h)	ISO 62	%	0,2
<u>MECHANICAL PROPERTIES</u>			
Tensile Stress at Break	ISO 527	MPa	26
Elongation at break	ISO 527	%	40
Tensile Modulus	ISO 527	MPa	2200
Flexural Modulus	ISO 178	MPa	2100
Flexural Strength	ISO 178	MPa	69
Charpy Impact Strength, notched 23 °C	ISO 179	kJ/m ²	10
Charpy Impact Strength, notched 0 °C	ISO 179	kJ/m ²	4,2
Charpy Impact Strength, unnotched 23 °C	ISO 179	kJ/m ²	No break
Charpy Impact Strength, unnotched 0 °C	ISO 179	kJ/m ²	No break
Rockwell Hardness R scale	ASTM D 785		115
<u>THERMAL PROPERTIES</u>			
Vicat Temperature for 1 kg	ISO 306	°C	83
Vicat Temperature for 5 kg	ISO 306	°C	78
Deflection temperature for 0,45 Mpa	ISO 75	°C	72
Deflection temperature for 1,8 Mpa	ISO 75	°C	68
Coefficient of linear thermal expansion	ASTM D 696	mm/mC	0,07
<u>ELECTRICAL PROPERTIES</u>			
Dielectrical Constant for 1 kHz	ASTM D 150		2,6
Dielectrical Constant for 1MHz	ASTM D 150		2,4
Dielectrical Strength	ASTM D 149	KV/mm	16,1
<u>OPTICAL PROPERTIES</u>			
Light Transmission (2 mm)	ASTM D 1003	%	88
Haze (2 mm)	ASTM D 1003	%	<2
Refractive Index	ASTM D 542		1,57
<u>FLAMMABILITY</u>			
Fire Resistance	UL 94		3 mm> 94V-2 3mm< 94 HB

These data are presented only as typical properties of the base resins which, to our best knowledge, are true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guaranty or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.