

Product Data – ACM TL



Dimensional Tolerances

Panel Thickness	+/- .008"
Aluminum Thickness	+/- .0008"
Width	-0; +.08"
Length	-0; +.12"
Diagonal	+/- .20"

Surface Properties

Paint	PE (Polyester) Digital Brushed/ Digital Brushed
Paint Thickness	17-20 microns
Pencil Hardness	≥2H
Toughness of Coating	≤2T
Impact Strength	30kg*cm (no crack in paint)
Boiling Water Resistance	Boiling for 2 hours no change
Solvent Resistance	Cleaned 200 times with Dimethylbenzene without change
Acid resistance	Immerse surface in 2%HCL for 24 hours without change
Alkali resistance	Immerse surface in 2%NaOH for 24 hours without change
Cleaning resistance	>1000 times without change
Peel Strength	≥3N/mm

Mechanical Properties

Sound Absorption NRC	0.05
Sound Attenuation RW DB	24
Water Absorption % By Volume	0.01
Core Composition	Polyethylene

These data are presented only as typical properties of the base resins which, to our best knowledge, are true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guaranty or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.