

Product Data - CR Type 1 PVC



Data sheet update	09.09.2019
Specific Gravity, g/cc , D792	1.41
Water Absorption, % , D570	<0.02
Tensile Strength at yield, psi , D638	9,000
Tensile Modulus, psi , D638	486,000
Izod Impact (notched), ft.lbs./in. , D256	0.8
Shore Hardness D, D2240	84
Continuous Service Temperature (Maximum), °F	140
Coefficient of Thermal Expansion, in./in./°F , D696	4.4×10^{-5}
Heat Deflection Temperature at 264 psi, °F , D648	154
Regulatory Code	UL 94 V0
Flammability UL 94	V-0, 5V

These data are presented only as typical properties of the base resins which, to our best knowledge, are true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guaranty or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.