

Product Data - HDPE Starboard



Properties	Units	ASTM	Nominal Values
Density	g/cc	D1505	0.955
Tensile Strength @ Yield	psi	D638	>4,100
Tensile Modulus	psi	D638	255,000
Elongation @ Break	%	D638	>600
Elongation @ Yield	%	D638	9.8
Flexural Modulus	psi	D790	185,000
Flexural Stress @ 5% Strain	psi	D790	3,810
Compressive Properties 10% Strain	psi	D695	4,950
Durometer	Shore D	D2240	68
Tensile Impact	ft.lbs./in. ²	D1822	115
Izod Impact Resistance	ft.lbs./in. ²	D256	1.1
Brittleness Temp.	°C (°F)	D746	<-76°C (<-105°F)
Vicat Softening Temp.	°C (°F)	D1525	128°C (262°F)
Heat Deflection Temp. 66 psi	°C (°F)	D648	99°C (210°F)
Screw and Nail Withdrawal	lbs	D1761	657 & 63
Flammability	Rating	UL94	HB

All values are determined on specimens prepared according to ASTM standards.

Nominal values should not be interpreted as specifications.

HDPE Starboard is made entirely from FDA and USDA approved material.

HDPE Starboard meets ASTM D4976.

The raw material used to make HDPE Starboard does not contain BPA's or Phthalates.

PLASTICS, INC.

These data are presented only as typical properties of the base resins which, to our best knowledge, are true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guaranty or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.