

Product Data - Type 1 PVC



Property	Units of Measure	Value	ASTM Method
Physical			
Density	g/cm ³	1.42	D 792
Water Absorption	%	0.06	D 570
Rockwell Hardness	R Scale	115	D 785
Shore Durometer	D	89	D 224
Cell Class	-	12454-B	D 1784
Mechanical			
Tensile Modulus	psi	411,000	D 638
Yield Strength	psi	7,500	D 790
Flexural Modulus	psi	481,000	D 790
Yield Strength	psi	12,800	D 790
Izod Impact Strength	ft-lb/in	1.0	D 256
Thermal			
Vicat Softening Point	°C/°F	83/181	D1525
Heat Deflection Temp (66 psi)	°C/°F	82/179	D 648
Heat Deflection Temp (264 psi)	°C/°F	80/176	D 648
Coefficient of Linear Expansion	in/in/°C	5.8 x 10 ⁻⁵	D 696
Coefficient of Linear Expansion	In/in/°F	3.2 x 10 ⁻⁵	D 696
Flammability Ratings			
Flame Spread Index	—	20	E 84
Flammability	—	0	UL 94V
Flammability	—	Self Extinguishing	D635
Chemical			
Chemical Resistance	—	Class B	D 1784
Electrical			
Electrical Volume Resistivity	Ohm/cm	5.4 x 10 ¹⁵	D 257
Dielectric Constant	60 Hz	3.9	D 150
Dissipation Factor	60 Hz	0.0096	D 150
Loss Index	60 Hz	0.030	D 150
Dielectric Strength	Volts / mil	544	D 149

These data are presented only as typical properties of the base resins which, to our best knowledge, are true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guaranty or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.