

Product Data - Vinyl Strip Door



PROPERTY	STANDARD	UNIT	VALUE
Shore A hardness	EN ISO 868	Sh A	80
Tearing resistance	DIN 53515	N/mm	50
Tensile strength at break	ASTM D 638 EN ISO 527	N/mm ²	16
Elongation at break		%	340
Residual elong. (after break)		%	68
Thermal conductivity	ASTM C 177	W/m.K	0.16
Cold bend brittle temperature	ISO 8570	°C	-35
Usage temp. range	EN 1876	°C	-15/+50
Vicat softening temp.	EN ISO 306	°C	50
Specific heat capacity	ISO 11357	kJ/kg.K	1.6
Sound reduction	DIN 52210	dB	>35
Reaction to fire	NF P 92-507 AS/NZS 3837 DIN 4102	Grade	Grp4 B2
Light transmittance	ASTM D 1003	%	85
UV/IR filter	EN 1598	Filter	-
UV resistance	ISO4892	-	Yes
Charge buildup	IEC 61087	Sparks	Yes
Surface resistivity	IEC 60093	.1012 Ω/□	40
Water Absorption	EN ISO 62	%	-0.2
Density	ASTM D 792	g/cm ³	1.22

These data are presented only as typical properties of the base resins which, to our best knowledge, are true and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guaranty or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing or future patents.